Milliken[®]

ResQ[™] CoreCXP[™]

Style 108001 ResQ™ CoreCXP™ Thermal Liner

MPG S000108001

Layer 1: MPG S000106138 Synergy 3.3 oz Plain, Fiber Content: 93% Nomex/5% Kevlar/2% P-140

Layer 2: S/723 2.3 oz E89 Spunlace Layer 3: S/715 1.5 oz E89 Spunlace

Quilted Thermal Liner	Process Average	Specs	Test Method
Weight	7.5 oz/yd²	≥ 7.0 oz/yd²	ASTM D3776
Width - (cuttable)	61.0"	≥ 60" cuttable	ASTM D3774
Trap Tear Strength, lbf (W x F)	53 x 31	≥ 5 x ≥ 5	ASTM D5587
Trap Tear Strength, lbf (W x F) after 5 launderings	59 x 37	≥ 5 x ≥ 5	ASTM D5587
Laundry Shrinkage, % (W x F) after 5 launderings	3.5 x 1.6	≤ 5 x ≤ 5	AATCC 135 - 1, V, Ai
Flame Resistance Test 1 Char Length, in (W x F) Afterflame, sec (W x F) Burn Observation (W x F)	1.7 x 1.3 0.0 x 0.0 No melt or drip	$\leq 4.0 \times \leq 4.0$ $\leq 2.0 \times \leq 2.0$ Shall not melt or drip	ASTM D6413
Flame Resistance Test 1 Char Length, in (W x F) Afterflame, sec (W x F) Burn Observation (W x F) after 5 launderings	1.3 x 1.1 0.0 x 0.0 Does not melt or drip	$\leq 4.0 \times \leq 4.0$ $\leq 2.0 \times \leq 2.0$ Shall not melt or drip	ASTM D6413 AATCC 135 - 1, V, Ai
Heat & Thermal Shrinkage Resistance Test, % (W x F)	0.5 x 0.0 Does not melt, drip, separate or ignite	≤ 10.0 x ≤ 10.0 Shall not melt, drip, separate or ignite	NFPA 1971 (section 8.6.5)
Heat & Thermal Shrinkage Resistance Test, % (W x F) after 5 launderings	0.5 x 0.0 Does not melt, drip, separate or ignite	≤ 10.0 x ≤ 10.0 Shall not melt, drip, separate or ignite	NFPA 1971 (section 8.6.5) AATCC 135 - 1, V, Ai

UL® certified to NFPA 1971



Note: "Process Averages" are historical averages; actual results may vary by lot (but will meet the min. "Specs.") Guaranteed flame resistance for the life of the garment (when washed according to care instructions).

These fabrics are innovative, flame resistant materials intended to be used in garments that supplement personal protective equipment and are engineered to self-extinguish when the source of ignition is removed. They may be used as a layer of, but are not intended for use as the primary protection in, firefighting garments or other products subject to repeated or extended exposure to heat or flame (unless explicitly certified in writing to meet the relevant regulations for use in such firefighting garments). As each customer's use of our product may be different, information we provide, including without limitation, recommendations, test results, samples, care/labeling/processing instructions or marketing advice, is provided in good faith but without warranty and without accepting any responsibility/liability. All sales are exclusively subject to our standard terms of sale posted at www.milliken.com/terms (all additional/different terms are rejected) unless explicitly agreed otherwise in a signed writing.

VERSION 5: September 2020

